

SCHEMA TECNICA
TECHNICAL CARD

Articolo / Article	Country Flower
Codice Articolo / Article Code	
Composizione / Composition	100 % PL
Peso Gr/mlt / Weight Grs/lmt	510 (+/- 5%)
Altezza cm / Width cms	140



Test Martindale UNI EN ISO 12947 - 2 EN 14465, appendix A	Colour degradation after 3000 rubs: 50.000 Giri / Rubs
---	--



Solidità Luce / Colour Fastness to light UNI EN ISO 105-B02 Blue Scale 1/8	4
--	----------

Solidità Sfregamento / Colour Fastness to rubbing UNI EN ISO 105-X12 Gray Scale 1/5	4 Secco / Dry 3 Umido / Wet
---	--

Test Pilling UNI EN ISO 12945-2	Degradation average photographic scale 1/5: 4 4 a 2000 giri / at 2000 revs
------------------------------------	---

Manutenzione / Maintenance

Note/Notes: Dimensional stability to dry washing (UNI EN ISO 3175)
warp: +/- % weft: +/- %
Dimensional stability to washing (UNI EN ISO 6330)
warp: +/- % weft: +/- %

* The results are tested in the laboratory and they must be considered as indicative.