

**SCHEMA TECNICA**  
**TECHNICAL CARD**

|                                |              |
|--------------------------------|--------------|
| Articolo / Article             | Country      |
| Codice Articolo / Article Code |              |
| Composizione / Composition     | 100 % PL     |
| Peso Gr/mlt / Weight Grs/lmt   | 510 (+/- 5%) |
| Altezza cm / Width cms         | 140          |

|   |  |
|---|--|
| Test Martindale<br>UNI EN ISO 12947 - 2<br>EN 14465, appendix A | Colour degradation after 3000 rubs:<br><b>75.000</b> Giri / Rubs |
|---|--|

|  |          |
|--|----------|
| Solidità Luce / Colour Fastness to light<br>UNI EN ISO 105-B02<br>Blue Scale 1/8 | <b>4</b> |
|--|----------|

|   |  |
|---|--|
| Solidità Sfregamento / Colour Fastness to rubbing<br>UNI EN ISO 105-X12<br>Gray Scale 1/5 | <b>4</b> Secco / Dry<br><b>3</b> Umido / Wet |
|---|--|

|                                    |   |
|------------------------------------|---|
| Test Pilling<br>UNI EN ISO 12945-2 | Degradation average photographic scale 1/5: <b>4</b><br><b>4</b> a 2000 giri / at 2000 revs |
|------------------------------------|---|

Manutenzione / Maintenance







Note/Notes: Dimensional stability to dry washing (UNI EN ISO 3175)  
warp: +/- % weft: +/- %  
Dimensional stability to washing (UNI EN ISO 6330)  
warp: +/- % weft: +/- %

\* The results are tested in the laboratory and they must be considered as indicative.